

REFRACTORY MAGNESITE TUNNEL KILN

FEUERFESTKERAMIK TUNNELOFEN FÜR BASISCHE STEINE
REFRACTARIOS HORNO TÚNEL PARA MAGNESITA




RIEDHAMMER

TW



MAGNESITE TUNNEL KILN (TW) FOR FIRING MAGNESITE PRODUCTS
TUNNELOFEN (TW) ZUM BRENNEN VON MAGNESIT-PRODUKTEN
HORNO TÚNEL PARA MAGNESITA (TW) PARA LA COCCIÓN DE PRODUCTOS DE MAGNESITA



Width (m) Breite Anchura	Length (m) Länge Longitud	Burner n° Brenneranzahl N° quemadores	Capacity (t/d) Kapazität (t/Tag) Capacidad (t/d)	
			1700°C	1800°C
1,2	50,4	224	20	22
1,2	60,0	28	24	26
1,2	69,6	32	28	30
1,6	60,0	28	32	34
1,6	69,6	32	37	40
1,6	79,2	36	42	45
2,0	74,4	34	50	53
2,0	84,0	38	56	60
2,0	93,6	42	62	67
2,0	103,2	46	69	73
2,4	93,6	42	75	80
2,4	103,2	46	83	88
2,4	112,8	50	90	96

TECHNICAL DATA	TECHNISCHE DATEN	DATOS TÉCNICOS	Capacity (t/d) Kapazität (t/Tag) Capacidad (t/d)	
			1700°C	1800°C
Firing cycle	Brennzyklus	Ciclo de cocción	72 h	72 h
Setting height*1	Setzhöhe	Altura de carga	0,8 m	0,8 m
Setting density*2	Setzdichte	Densidad de carga	1,5 t/m	1,6 t/m

*1 possible values: 0,6 and 0,8

*2 for product density >3,0=1,6; for <3,0=1,5;

Riedhammer GmbH Industrial kiln plants

postal address: 90332 Nürnberg - Germany / address: Klingenhofstraße 72, 90411 Nürnberg - Germany
 telephone: +49.911.52180 / fax: +49.911.5218231 / e-mail: mail@riedhammer.de / web: www.riedhammer.de